



카탈로그



On-Line
Sample Book



DECOCLICK (LVT Click 4.0T/0.55mm)

TECHNICAL DATA SHEET

LG Hausys DECOCLICK meets the requirements of EN ISO 10582 (EN | FR | DE | SP)

Characteristic	Standard	Unit	Results
Type of Flooring	Type de sol Bodentyp Tipo de pavimento	EN ISO 10582	PVC Heterogeneous Tile
Surface Treatment	Traitement de Surface Oberflächenbehandlung tratamiento de superficies		High Density PUR
Classification	Classe d'usage Klassifizierung Clase de uso	EN ISO 10582	Class 23/33/42
Weight	Poids Flächengewicht Peso total	EN ISO 23997	g/m ² 6,800
Size	Dimensions Maße Medidas	Possible Spec	
- Planks	Lames Dielen Lamas	mm	150×1220
- Tiles	Dalles Fliesen Losetas	mm	310×605
Squareness : Straightness	Rectitude Geradheit Rectitud	EN ISO 24342	% ≤0.25
Overall Thickness	Epaisseur totale Gesamtdicke Espesor total	EN ISO 24346	mm 4.0
Wear Layer Thickness	Epaisseur de la couche d'usure Dicke Nutzschicht Espesor de la capa de uso	EN ISO 24340	mm 0.55
Wear Resistance	WGroup d'abrasion Verschleißverhalten Resistencia a la abrasión	EN 660-2	T
Residual Indentation	Poinçonnement rémanent Resteindruckverhalten Punzonamiento estático residual	EN ISO 24343-1	mm ≤0.1
Dimensional Stability	Stabilité dimensionnelle Dimensionsstabilität Estabilidad dimensional	EN ISO 23999	% ≤0.15
Curling after exposure to heat	Incurvation Schüsselung Curvado	EN ISO 23999	mm ≤1
Light Fastness	Résistance la lumière Lichtechtheit Resistencia de los colores a la luz UV	EN ISO 105-B02	≥6
Furniture Leg Resistance	Résistance au pied de meuble Verschiebung eines Möbelstuhls Resistencia a las patas de los muebles	EN 424	No Crack, No Damage
Castor Chair Resistance	Résistance aux chaises roulettes Stuhlrollenbeanspruchung Resistencia a sillas con ruedas	EN ISO 4918	No Change
Reaction to fire	Classement feu Brandverhalten Resistencia al fuego	EN 13501-1	Bfl-s1
Stain Resistance	Résistance aux taches Fleckenbeständigkeit Resistencia a las manchas	EN ISO 26987	No Change PUR Surface Treatment
Slip Resistance	Glissance Rutschfestigkeit Resistencia al deslizamiento	DIN 51130	R9/R10
Dynamic Coefficient of friction	Résistance au glissement Rutschhemmung Resistencia al deslizamiento	EN 13893	Class D5
Friction (Pendulum Test)	Friction Reibung Fricción	EN 13036-4	30/36†
Acoustic Insulation	Efficacité acoustique Trittschalldämmung Aislamiento acústico	EN ISO 10140	dB 5
Electrical Resistance	Résistance électrique Elektrischer Leitwiderstand Resistencia eléctrica	EN 1081	ohm ≤5.0×10 ¹¹
Electrostatic Performance	Accumulation de charges électrostatiques Antistatik Propiedades electrostáticas	EN 1815	kV ≤2
Thermal Resistance	Résistance thermique Wärmedurchlasswiderstand Resistencia térmica	EN 12667	m2.K/W 0.04
Underfloor Heating	Chauffage par le sol Fußbodenheizung Calefacción radiante		Suitable, Max 27°C 80.6°F
Warranty In Years	Garantie en années Garantie in Jahren Garantía en años	EN 12524	10 Commercial, 30 Residential
Formaldehyde Group	Classe formaldéhyde Formaldehyd Klassifizierung Clase de formaldehído	EN 717-1	E1
Phthalate Free	Sans phtalate Phthalatfrei Libre de ftalato		N.D
Heavy metal Free	Heavy metal gratuit Schwermetallfrei Heavy metal Free		N.D
CE Marking	Marguage CE CE Kennzeichnung Marcado CE	EN 14041:2004/AC:2006	DOP N°20EDC-DOP-40
TVOC After 28 Days	TVOC après 28 jours TVOC (28 Tage) TVOC (28 dagen) Compuestos Orgánicos Volátiles después	ISO 16000-06	A+ (Eurofins 392-201800200802)
REACH		N° SVHC	SGS AYAA18-62889
Length Flatness	Longueur à plat Länge Ebenheit Planeidad de la longitud	ISO10582/AnnexB	% ≤0.05%
Width Flatness	Largeur Planité Breite Ebenheit Planeidad da la anchura	ISO10582/AnnexB	% ≤0.05%
Opening(Average)	Ouverture Öffnung Apertura	ISO10582/AnnexC	mm Pass
Locking strength	Force de blocage Schließkraft Resistencia del sistema clic de cierre	ISO10582/AnnexD	mm Ave 3.0N



Engineered with Precision



www.lghausys.com

DECOCLICK

LVT CLICK



LVT CLICK



LG Hausys

DECOCLICK

40(T) × 150(W) × 1,220(L) mm

※ Each plank is unique in pattern and color and has been engineered to display a realistic visual.
※ Please make sure to check the color of the index sample with the original sample.



1227 Pale Buttermilk



1201 Stone Alloy



1206 Mild Persimmon



0030 Flaxen Gold



1267 Brown Sugar



1265 Wrought Iron



1266 Stained Pewter

DECOCLICK



On-Line
Sample Book



LVT CLICK



LG Hausys

DECOCLICK

40(T) × 150(W) × 1,220(L) mm

※ Each plank is unique in pattern and color and has been engineered to display a realistic visual.
※ Please make sure to check the color of the index sample with the original sample.



7821 Cinnamon Apricot



0024 Bleached Alabaster



2643 Corn Bisque



1253 Blonde Toffee



1207 Coastal Wood



1208 Merchant Timber



1258 Bordeaux Mountain

DECOCLICK

40(T) × 150(W) × 1,220(L) mm

※ Each plank is unique in pattern and color and has been engineered to display a realistic visual.
※ Please make sure to check the color of the index sample with the original sample.



0026 Vanilla Bean



1228 Salted Cream



2609 Ivory Coast



7820 Rosy Mist



1270 Casted Shadow



0025 Warm Carbon



1203 Dandelion